



LONDON METAL EXCHANGE

Special Contract Rules for High Grade Primary Aluminium

Quality: In conformance with either of the following specifications (A) and (B) but note that with effect from 1st January 2010 LME Warrants may only be issued that demonstrate conformance with Specification (B).

(A) Primary Aluminium of Specification:

Element	Composition, % maximum
Si	0.10
Fe	0.20
Aluminium	99.70 % minimum

(B) The Aluminum Association Inc International Designations and Chemical Composition Limits for Unalloyed Aluminium; P1020A (March 2007).

Element	Composition, % maximum
Si	0.10
Fe	0.20
Zn	0.03
Ga	0.04
V	0.03
Others Each **	0.03
Others Total **	0.10
Aluminium	Remainder

** There is no requirement within the Specification to establish the composition values of any other specific element.

4 March 2009